GRAFT POLYMER
COMBINE INCOMPATIBLE

TDS | Technical Data Sheet

GRAFTABOND™ UHP 00030G | Compatibilizer

Product Description

GRAFTABOND™ UHP 00030G is an ultra-high-molecular-weight polyethylene (UHMWPE) powder grafted with glycidyl methacrylate (GMA), used as a compatibilizer and impact modifier for engineering polyesters and epoxy-based thermosets. Made by solid-phase grafting: the monomer is grafted onto the polymer powder below its melting point.

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Physical Form	powder	
Bound GMA	3 wt %	FTIR (Internal Method)
Moisture (loss on drying) 105 °C	< 0.5 %	ASTM D6980

Applications

Raises the impact strength of thermoplastic and thermosetting polyesters.

The epoxide groups react with the carboxyl end groups of polyesters.

Processing & Dosage

GRAFTABOND™ UHP 00030G is processable on most thermoplastic processing equipment.

Preferred for: Extrusion (Compounding)

Typical dosage: 1–4 % (as supplied) of the total formulation. These levels are for orientation only; the optimal content should be determined experimentally.

Storage and Transportation

Store at no more than 35 °C and below 80 % relative humidity. Avoid direct sunlight and contact with water.

Normally packed in 25 kg bags (50 bags per pallet).

Shelf Life

12 months from the date of delivery, in unopened packaging. For any use above this limit, please refer to our technical services.

GRAFT POLYMER D.O.O.
Struge 18, Borovnica 1353 Slovenia
Company Num. 8056200000, VAT. SI 30561345
info@graftpolymer.com

The data listed here falls within the normal range of properties, but they should not be used to establish specification limits nor used alone as the basis of design. The GRAFT POLYMER Company assumes no obligations or liability for any advice furnished or for any results obtained with respect to this information. All such advice is given and accepted at the buyer's risk. The disclosure of information herein is not a license to operate under, or a recommendation to infringe, any patent of GRAFTABOND™ or others. Since GRAFT POLYMER cannot anticipate all variations in actual end-use conditions, GRAFT POLYMER makes no warranties and assumes no liability in connection with any use of this information.